



French Wood



venture



Made in the USA

French Wood Collection



Digital Technology

A new glazing technology which allows for no repetition and a natural effect through high resolution, computer generated images and consistent shading production.

French Wood Collection



8 x 48
IRG0848121

6 x 24
-

Beech



8 x 48
IRG0848123

6 x 24
IRG0624123

Larch

Trim



Bullnose
6 x 24

Beech

IRG624BT121

Larch

IRG624BT123



Beech 8" x 48"



Larch 8" x 48"



Beech 6" x 24"





Larch 6" x 24"

C1028
COF
Dry ≥ 0.80
Wet ≥ 0.60

Acutest
COF
Wet ≥ 0.42

French Wood Tech Specs

PHYSICAL PROPERTIES	TEST	INDUSTRY STANDARDS	IRIS US RESULTS COLORED BODY
Water Absorption	ASTM C373	0.5% Maximum	$\leq 0.1\%$
Size			
Calibrated (non rectified)	ASTM C499	• Range of Thickness (inch) 0.040	≤ 0.040
	ASTM C499	• Average Facial Dimension $\pm 0.50\%$	$\leq \pm 0.50\%$
	ASTM C485	• Warpage $\pm 75\%$ on any edge	$\leq \pm 0.75\%$
	ASTM C485	• Warpage $\pm 50\%$ on diagonal	$\leq \pm 0.50\%$
	ASTM C502	• Wedging $\pm 0.50\%$	$\leq \pm 0.50\%$
Rectified	ASTM C499	• Range of Thickness (inch) 0.040	≤ 0.040
	ASTM C499	• Average Facial Dimension $\pm 0.25\%$	$\leq 0.25\%$
	ASTM C485	• Warpage $\pm 0.40\%$ on any edge	$\leq 0.40\%$
	ASTM C485	• Warpage $\pm 0.40\%$ on diagonal	$\leq 0.40\%$
	ASTM C502	• Wedging $\pm 0.25\%$	$\leq 0.25\%$
Bond Strength	ASTM C482	50 psi or greater	> 200 psi
Deep Abrasion	ASTM C1243	< 175 mm ³	< 150 mm ³
Hardness (Mohs scale)		No requirement	≥ 7
Frost Resistance (Freeze/Thaw)	ASTM C1026	No sample must show alterations to surface	No cracking or spalling occurred
Chemical Resistance	ASTM C650	No requirement	Class A
Breaking Strength	ASTM C648	250 lbf or greater	≥ 350 lbf
Coefficient of Friction (static)	ASTM C1028	No requirement	Per collection

Data taken from a representative colored body collection. Individual product testing can be conducted by request.

Coefficient of Friction: All values given are for matte or honed material. No values are given for polished material. Iris U.S. does not recommend polished surfaces in areas subject to exposure from grease, oil or water. (All values are based on ASTM C1028 and Acutest DCOF.)

French Wood Packaging

PRODUCT	SIZE	BOX PIECES	BOX SF	PALLET BOXES	PALLET SF	THICKNESS	WEIGHT LB/SF
Floor & Wall Tile	8 x 48	6	15.585	32	498.72	8	3.55
	6 x 24	16	15.585	40	623.4	8	3.55
							LB PER PIECE
Bullnose	6 x 24	16	15.585	-	-	8	3.55